

DERWENT- 2002-455219

ACC-NO:

DERWENT- 200249

WEEK:

COPYRIGHT 2009 DERWENT INFORMATION LTD

TITLE: Hydraulic binder for clarifier basins or channel linings
comprises a latently hydraulic bulky blast furnace slag
containing sulfate promoter and activating additives

INVENTOR: NOVAK D

PATENT- NOVAK D[NOVAI] , WOPFINGER STEIN & KALKWERKE

ASSIGNEE: SCHMID[WOPFN]

PRIORITY-DATA: 2000US-695447 (October 24, 2000)

PATENT-FAMILY:

PUB-NO PUB-DATE LANGUAGE

CA 2324486 A1 April 24, 2002 EN

APPLICATION-DATA:

PUB-NO APPL-DESCRIPTOR APPL-NO APPL-DATE

CA 2324486A1 N/A 2000CA-2324486 October 26, 2000

INT-CL-

CURRENT:

TYPE IPC DATE

CIPS C04 B 7/21 20060101

RELATED-ACC-NO: 2002-373768

ABSTRACTED-PUB-NO: CA 2324486 A1

BASIC-ABSTRACT:

NOVELTY - A hydraulic binder comprises a latently hydraulic bulky blast furnace slag, finely ground to in excess of 5000 cm²/g Blaine, containing a sulfate promoter and activating additives.

DESCRIPTION - The latently hydraulic bulky blast furnace slag has greater than 93% glassiness and contains (wt.%) silicon dioxide (SiO₂) (34-40), calcium oxide (CaO) (34-37), aluminum oxide (Al₂O₃) (greater than 9), and (CaO+magnesium oxide)/(Al₂O₃+SiO₂) (0.88-0.98).

USE - For clarifier basins, channel linings, clarifier plants, collection basins and building structures.

ADVANTAGE - The invention yields good products and has very low hydration heat.

EQUIVALENT-ABSTRACTS:

INORGANIC CHEMISTRY

Preferred Composition: The content (wt.%) of Al₂O₃ in the blast furnace slag is at most 13 wt.%. The binder contains calcium sulfate (CaSO₄) (12-20) recovered by settling from a flue gas desulfurization or a hemihydrate or their anhydrite and/or natural CaSO₄. It also contains hot dust, hydrated lime or burned lime (0.5-3). It also contains alkali sulfate and/or alkali carbonate (up to 3).

Preferred Component: The alkali sulfate or alkali carbonate is potassium sulfate, sodium sulfate, sodium carbonate, lithium carbonate or potassium sulfate.

Preferred Property: The bulky blast furnace slag has a Blaine fineness of 5000-6500 cm²/g.

CERAMICS AND GLASS

Preferred Composition: The binder contains (wt.%) Portland cement clinker or Portland cement (0.5-5).

ORGANIC CHEMISTRY

Preferred Composition: The binder comprises calcium (Ca) salt of carboxylic acid (0.5-3). Preferred Component: The Ca salt of carboxylic acid is calcium acetate and/or calcium formate.

TITLE- HYDRAULIC BIND CLARIFY BASIN CHANNEL LINING COMPRISE LATENT
TERMS: BULK BLAST FURNACE SLAG CONTAIN SULPHATE PROMOTE ACTIVATE
ADDITIVE

DERWENT-CLASS: L02 M24

CPI-CODES: L02-B03; L02-C; M24-A07B;

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: 2002-129497